



شماره تماس:  
۰۹۱۰ ۳۳۰ ۴ ۹۹۰

- واردات و فروش انواع دستگاه تزریق پلاستیک
- فروش انواع مواد اولیه پلیمر وارداتی و داخلی
- فروش انواع گرانول، مسترچ و کامپاندهای تخصصی



## MOPLEN MR230C



MOPLEN MR230C is a polypropylene random copolymer grade, designed for hot and cold water supply systems. It is also suitable for industrial water conveyance.

The material has excellent creep properties and processability by extrusion and by injection molding.

TYPICAL PROPERTIES (a)	ISO (b) METHOD	UNIT	VALUE	ASTM(b) METHOD	UNIT	VALUE			
<b>Physical properties</b>									
Melt flow rate (190 °C, 5 kg)	R 1133	g/10 min	0.4 - 0.6	D 1238 L	g/10 min	0.4 - 0.6			
Melt flow rate (230°C, 2.16 kg)	R 1133	g/10 min	< 0.3	D 1238 L	g/10 min	< 0.3			
Melt flow rate (230°C, 5 kg)	R 1133	g/10 min	0.8 - 1.3	D 1238 L	g/10 min	0.8 - 1.3			
Hardness Rockwell	R 2039/2	R scale	93						
Linear coefficient of expansion				D 696	mm/(mx°C)	0.11			
Thermal conductivity (23°C)	R3146	W/(mxK)	0.17						
Specific gravity	R1183	-	0.89	D 792	-	0.89			
<b>Mechanical properties</b>									
Flexural modulus	R 178	MPa	835	D 790	MPa	950			
Tensile strength at yield	R 527	MPa	28	D 638	MPa	28			
Elongation at break	R 527	%	>430	D 638	%	>430			
Notched Izod impact strength	R 180/1A	kJ/m <sup>2</sup>	at 23°C	NB	D 256	J/m	at 23°C	NB	
			at 0°C				at 0°C		160
			at -20°C				at -20°C		50
Unnotched Izod imp. Strength	R 180/1A	kJ/m <sup>2</sup>	at 23°C	NB	D 256	J/m	at 23°C	NB	
			at 0°C				at 0°C		NB
<b>Thermal properties</b>									
Vicat softening point (9.8N)	R 306	°C	135	D 1525	°C	135			
H.D.T. (0.45 Mpa)	R 75	°C	80	D 648	°C	80			
Accelerated oven ageing at 135°C	R 4577	hours	>9,000	D 3012	hours	>9,000			

a) Values shown are averages and not to be considered as product specifications. These values may shift slightly as more data is accumulated

b) ASTM and ISO test methods are the latest under the society current procedures. All specimens are prepared by injection